

EXHIBIT A

List your Company | List as an Expert | Pl




Where small quantities
make **BIG IDEAS** come to

- Home / Search
- New Journal - Azom
- MyAzom
- Materials
- Applications
- Industries
- Quality Control Diary
- Course Diary
- Publication Diary
- Industry News
- Books
- Media Packs
- Azom Info
- Our Partners
- Help/FAQ's
- Terms and Privacy

**Gemini
HR nano
Rheometer**

From **Malvern
Instruments**



Featured Courses

Advanced Materials Masters
Course



Thermoplastics - An Introduction

Topics Covered

Background

Thermoplastic Characteristics

Amorphous Polymers

Semi-Crystalline Polymers

Background

What is an engineering thermoplastic? Such a definition is difficult to arrive at and is very subjective, but, for the purposes of this review article, any thermoplastic that can be formed into a load-bearing shape that might otherwise be formed from, for example, steel or wood will be classed as an engineering thermoplastic. This review is restricted to unreinforced and short fibre reinforced thermoplastics where the reinforcing fibre (usually glass or carbon) is typically less than 2-3 mm in length.

Thermoplastics offer many advantages over traditional materials, including: low density; low energy for manufacture; low processing costs; and the ability to make complex shapes relatively easily.

Thermoplastic Characteristics

Thermoplastic materials generally fall within two classes of molecular arrangement, amorphous and semi-crystalline (see figure 1).

Small to a friend
Buyers

Books

Books

Books

ABM International
Characterization and
Failure Analysis of
Plastics

Taylor & Francis

Advanced Polymeric
Materials; Structure
Property Relationships

Composites
Manufacturing:
Materials, Product, and
Process Engineering

At the Google

Low Density
Polyethylene
Sheeting, Films, CP,
Construction
All printing and colors
available
www.univpack.com/ldep-plastic

Plastics Properties
Technical datasheets for
Polymers
and properties profiles
www.Omnexus.com

Baker Petrolite Polymers
Performance Polymers
Additives for Industry
www.polywax.com

Minigrip Bags Now 75%
Off
FDA-approved reclosable
poly
2&4 mil white stripe
factory direct
www.minigripdirect.com

Plastic Resin Distributor
Polypropylene,
Polyethylene

<http://www.azom.com/details.asp?ArticleID=83&head=Thermoplastics%2B-%2BAn%2BI...> 12/7/2005

PAGE 23/32 * RCVD AT 12/22/2005 8:35:34 PM [Eastern Standard Time] * SVR:USPTO-EFXRF-6/26 * DNIS:2738300 * CSID:8013281707 * DURATION (mm:ss):12:20

BEST AVAILABLE COPY

Thermoplastics - An Introduction

Page 2 of 5

Microsystems and Nanotechnology
MarketsPolymer Science and Technology -
5 Day Course

Software Engineering


Partners
Nanotechnology

Eng-Tips Forum

Medical News

Building/Construction

Amorphous



Semi-crystalline



Polystyrene, Wide Spec
Virgin
www.globaltrafficinc.comThermal Conduct.
Plastics
Resource for thermally
conductive
thermoplastics in
electrical parts
www.cncaptech.comChemical Manufactures
Chemical Petrochemical
B2B listings
products suppliers
manufactures
sulekhab2b.comBuy Polyethylene Online
Alastian, no-frills quality
PP & PE
See real-time prices.
Register Now!
www.alastian.com**Figure 1** Molecular Arrangement of Polymer
ChainsTable 1 lists a selection of amorphous and semi-
crystalline polymers.**Table 1.** Amorphous and semi-crystalline
polymers.

Amorphous	Semi-crystalline
Polyamideimide	Polyetheretherketone
Polyethersulphone	Polytetrafluoroethylene
Polyetherimide	Polyamide 6,6
Polyarylate	Polyamide 11
Polysulphone	Polyphenylene sulphide
Polyamide (amorphous)	Polyethylene terephthalate
Polymethylmethacrylate	Polyoxymethylene
Polyvinylchloride	Polypropylene
Acrylonitrile butadiene styrene	High Density Polyethylene
Polystyrene	Low Density Polyethylene

Amorphous Polymers

Generally, fully amorphous polymers are stiff, brittle and clear in the virgin state. The temperature and stress state have a profound effect on the molecular arrangement and hence the properties of a polymer. Under the action of sufficient stress, the polymer chains can uncoil and align over a period of time. At elevated

temperatures, polymer chains have enough energy to rotate and coil up further.

Figure 2 shows schematically the effect of temperature on the elastic modulus of an amorphous and a semi-crystalline polymer. Below a temperature known as the glass transition temperature, T_g , the structure of amorphous polymers is termed 'glassy', with a random arrangement of the polymer chains, similar to the random molecular arrangement found in glass. As the temperature increases to T_g , the polymer chains have sufficient thermal energy to rotate, resulting in a drop in modulus. One definition of T_g is the temperature at which molecular rotation about single bonds becomes favourable as the temperature increases. At temperatures above T_g but below the melting temperature, T_m , there is a 'rubbery region', where the material can exhibit large elongations under relatively low load. Amorphous thermoplastics are generally used at temperatures below their T_g , where they can be brittle, just like glass. There are, however, certain exceptions. Polycarbonate (PC) is amorphous yet it is considered tough at temperatures well below its T_g . When it does fracture below its T_g , it does so in a brittle manner, but this requires a large amount of energy and so PC is considered tough, finding use in applications requiring impact resistance, e.g. safety helmets and bullet proof glazing. This behaviour is due to the chemical bonds in polycarbonate rather than the arrangement of the polymer chains.




Figure 2. The effect of temperature on the Elastic Modulus (assuming both types of polymer have the same T_g and T_m)

Semi-Crystalline Polymers

Semi-crystalline materials such as polyamides do not exhibit a clear T_g or 'rubbery' region, although one is often quoted as the amorphous parts of the structure will undergo some transition. For these polymers the main transition occurs at T_m when the crystalline regions break down (see Fig. 2). Some chain rotation in the amorphous regions will occur below T_m, giving some impact resistance at these temperatures. Values of T_g and T_m for a number of polymers are given in Table 2.

Table 2. Glass transition and melting temperatures for a range of thermoplastics.

Polymer	T _g (°C)	T _m (°C)
High density polyethylene (HDPE)	-	135
Polypropylene (PP)	-10	175
Polystyrene (PS)	100	-
Polymethylmethacrylate (PMMA)	105	-
Polyvinylchloride (PVC)	65	-
Natural rubber (NR)	-75	25
Polydimethyl siloxane (PDMS)	-125	-55
Polyoxymethylene (POM)	125	175
Polycarbonate (PC)	150	-
Polyethylene terephthalate (PET)	70	265
Polyetheretherketone (PEEK)	145	335
Nylon 6 (PA6)	50	215
Polyamideimide (PAI)	295	-
Polysulphone (PSul)	195	-
Polyphenylene sulphide (PPS)	90	285
Polyethersulphone (PES)	230	-
Polyetherimide (PEI)	218	-
Polytetrafluoroethylene (PTFE)	20	325
Liquid crystal polymer (LCP)	-	420


Table 2. Values of T_g and T_m for selected polymers

Abstracted From the Materials Information Service, edited by Justin Furness

For more information on Materials Information Service please visit The Institute of Materials.



top



AZoM™ - Metals, Ceramics, Polymers, Composites, An Engineers Resource...AZoM™.com Pty.Ltd Copyright © 2000-2005